

TECHNICAL DATA SHEET

PETROLATUMS | VASELINES
Technical | Yellow & Brown

Usocore [®] Petrolatum	Drop Melting Point	Congealing Point	Needle Penetration	Colour Saybolt
	ASTM D127 °C	ASTM D938 °C	ASTM D937 Mm x 0.1 @25°C	ASTM D156
Petrolatum 17066	67	60	130	Brown
Petrolatum 17210	65	58	140	Yellow/Brown
Petrolatum 17266	55	55	150	Yellow/Brown
Yellow Technical I	61	52	164	Yellow/Brown
Petrolatum 5671	62	54	185	Yellow
Petrolatum 17169 Anti corrosion	35	33	185	Yellow
Petrolatum 1760 Anti-corrosion	35	34	170	Brown
Petrolatum 8732	79	68	80	Brown

All above grades are subject to usual tolerances.

Other viscosities or special grades are available on request.

EC Number (Einescs): 232-373-2 / CAS Number: 8009-03-8